## **AMENDMENTS TO THE ABSTRACT OF THE DISCLOSURE:**

Please amend the abstract as follows:

To lower the energy demand for melting in a unit with cooled walls, the invention provides a  $\underline{A}$  method for melting inorganic materials, preferably glasses and glass-ceramics, in a melting unit with cooled walls, in which method is provided. The method includes selecting the temperature of at least one region of the melt is selected in such a way as to be in a range from  $T_{eff}$  – 20% to  $T_{eff}$  + 20%, where the temperature  $T_{eff}$  is given by the temperature at which the energy consumption per unit weight of the material to be melted is at a minimum, with the throughput having been selected in such a way as to be suitably adapted to the required residence time.